

AGNES









221.01-221.10
221.01 221.10

Composition	100% PES		
Weight	570 g/m² ± 5%		
Width	142 ± 3 cm		
Туре	woven fabric		
Brand	upholstery fabric		
Abrasion resistance			

Ms.	Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 rubs	Α
	Fuzzing and pilling PN-EN ISO 12945-2:2002	4-5	А
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	А
;ċ:	Colour fastness to artificial light PN-EN ISO 105-B02:2014-11	4-5	С
	the mean of bursting strength PN-EN ISO 13938-1:2020-05	1040 kPa (the mean height at burst : 15 mm)	А
2	Cigarette test		1
	PN-EN 1021-1:2014-12		•

Maintenance















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented $% \left(1\right) =\left(1\right) \left(1\right)$ in the sampler.
- Manufacturer is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.