BRAID			
3001-3031		NON-FLAMMABLE	
Composition		100% PES	
Weight		320 g/m² ± 5%	
Width		142 ± 3 cm	
Туре		woven fabric	
Brand		upholstery fabric	
Abrasio	n resistance PN-EN ISO 12947-2:2017-02	100 000 rubs	A

	Fuzzing and pilling PN-EN ISO 12945-2:2002	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	4-5	A
	Seam slippage PN-EN ISO 13936-2:2005							5 warp 6 weft	В
	Wet rubbing PN-EN ISO 105-X12:2016-08							4-5	A
	Dry rubbing PN-EN ISO 105-X12:2016-08	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle \\ \langle \rangle$	$\langle \rangle$	4-5	A
9	Cigarette test PN-EN 1021-1:2014-12	$\langle \rangle$	$\langle \rangle \\ \langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle$	$\langle \rangle = \langle \rangle$		



- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning 1. of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric. 3.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used. 4.
- Due to friction against the fabric, colourants can migrate from darker to brighter -5. fabrics.
- Long-term exposure to sunlight can cause discolouration. 6.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge 7. of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.